




P.T.B.-ANTIGEL

For mortar
and concrete




Characteristics

- Bonding accelerator
- Plasticizing action
- Improves the strength
- Smooth from stripping



Dosage

- Add 2 L P.T.B.-ANTIGEL for 50 kg cement to the make-up water.
- Use P.T.B.-ANTIGEL only with Portland or blast furnace cement
- Use P.T.B.-ANTIGEL only at max. -5°C !



+30°

Remarks

-5°

- Cannot be used in armed concrete
- Contains chloride

Refer to clause p. 2.

Mixing ratio	Consumption	Packaging
Add undiluted to the make-up water	max. 2 l for 50 kg of cement	2 l (20 pcs/cardboard box), 5 l and 10 l
Colours		Application temperature
Colourless	Avoid contact with the skin	from - 5 till + 30 °C